

## auto electrical parts

### Technical Information Sheet

#### Part No. 0-329-03/04/06/09/12/19

Black heat shrink adhesive lined Polyolefin tubing, shrink ratio 3:1. Minimum shrink temperature 80°C. Operating temperature -45°C to +110°C.



#### Additional information

	I.D (mm)	W.T. (mm)
0-329-03	3.0	0.35
0-329-04	4.8	0.35
0-329-06	6.0	0.40
0-329-09	9.0	0.50
0-329-12	12.0	0.60
0-329-19	19.0	0.70

W.T. is wall thickness pre shrink.

Technical Drawing (not to scale)

Intentionally Blank

#### Specification

Type	Heat shrink adhesive lined tubing
Material	Ployoeфин
Colour	Black
Operating temperature	-45°C to +110°C
Min shrink temperature	+80°C
Min recovery temperature	+110°C
Shrink ratio	~3:1
Longitudinal shrinkage	≤10%
Insulation resitance	≥10 <sup>14</sup> Ωcm
Tensile strength	≥12.0MPa
Approvals	UL224 E255532

The information contained in this document is correct to the best of our knowledge at the time of printing. However, specifications may change at any time without notice.

#### Gordon Equipments Limited

Durite Works  
Valley Road  
Dovercourt  
Essex CO12 4RX  
England

Tel: +44 (0)1255 555200  
Fax: +44 (0)1255 555222  
E-mail: sales@durite.co.uk  
Web: www.durite.co.uk



Registered in England at address shown No. 373113  
The words 'Gordon', 'Durite', 'Nolten' and 'Acfil' are registered trade marks