

auto electrical parts

Technical Information Sheet

Part No. 0-333-02/03/04/06/09/12/19/25/38

Heat shrink Polyolefin tubing, flame retardent, shrink ratio 2:1. Minimum shrink temperature 70°C. Operating temperature of -55°C to 125°C.



	I.D (mm)	W.T. (mm)
0-333-02	2.5	0.20
0-333-03	4.0	0.25
0-333-04	5.0	0.25
0-333-06	6.0	0.28
0-333-09	9.6	0.30
0-333-12	12.7	0.30
0-333-19	19.0	0.40
0-333-25	26.0	0.45
0-333-38	37.0	0.50

W.T. is wall thickness pre shrink.

[Technical Drawing](#) (not to scale)

Intentionally Blank

Specification

Type	Heat shrink tubing
Material	Polyolefin
Colour	Black
Operating temperature	-55°C to +125°C
Min shrink temperature	+70°C
Min recovery temperature	+110°C
Shrink ratio	~2:1
Longitudinal shrinkage	≤ 5%
Dielectric strength	25KV/mm
Insulation resistance	≥10 ¹⁴ Ωcm
Approvals	UL224 E255532

The information contained in this document is correct to the best of our knowledge at the time of printing. However, specifications may change at any time without notice.

Gordon Equipments Limited

Durite Works
Valley Road
Dovercourt
Essex CO12 4RX
England

Tel: +44 (0)1255 555200
Fax: +44 (0)1255 555222
E-mail: sales@durite.co.uk
Web: www.durite.co.uk



Registered in England at address shown No. 373113
The words 'Gordon', 'Durite', 'Nolten' and 'Acfil' are registered trade marks